


Product: SPV 30800 series: SPV 308LA5, SPV 3088A5, SPV 30804

Product group: Surface Protection Tapes

General description

SPV 30800 series are surface protection tapes suitable to protect metal and plastic surfaces during mechanical processes, storage and transportation. These products consist of a PE film in various colours, coated with a pressure sensitive rubber-based adhesive.

Construction



- Pressure sensitive rubber-based adhesive
- PE film*

* SPV 308LA5: Black and white with blue co-extruded lines
SPV 3088A5: Clear transparent
SPV 30804: Black and white

Characteristics

These products protect the substrate till the end of the supply chain against scratches and impurities. The rubber-based adhesive is pressure sensitive and gives a medium adhesion level. These tapes have enough oil resistance and therefore usable to protect metals after milling operations. The blue co-extruded lines of SPV 308LA5 allow to position the treated substrate in the appropriate direction. These lines avoid ghost printing in contradiction to normal printing systems. The transparency of SPV 3088A5 allows easy identification and inspection of the protected substrates.

Application

SPV 30800 series are ideal products to protect metal surfaces such as stainless steel, anodised aluminium, coated metals and plastic substrates such as PMMA, Polystyrene, PVC and PC.

Features

- medium adhesion level
- blue lines (SPV 308LA5)
- recyclable
- substrate identification and inspection (SPV 3088A5)

Properties

	Typical Value	Test Method
Film type	PE film	
Adhesive type	Rubber-based	
Total thickness	80 µm	EN 1942
Adhesion on BA steel	100 cN/20 mm	EN 1939
Weatherability on BA steel*		ISO 4892-2
SPV 3088A5 (Clear transparent)	None	
SPV 308LA5 (Black/white with blue lines)	250 h	
SPV 30804 (Black/white)	250 h	
Tensile strength MD**	30 N/20 mm	EN 14410
Elongation MD	250 %	EN 14410
Transport and storage conditions	Temperature 15 to 30°C	
	Relative humidity 40 to 75% RH	

Details from the test methods are described on the customer product specification.

* The weatherability is measured on BA steel. Depending on the substrate the weatherability performance can be different.

** MD = Machine Direction

Warranty

The product is guaranteed to be free from defect in material and workmanship at the time of delivery and will be suitable for use for a period of 6 months thereafter, subject to the conditions set out herein.

Availability

Widths: 1000 mm, 1250 mm and 1500 mm

Lengths: 500 m and 1000 m

Please contact us for specific dimensions

Lamination guidelines

- The tapes should be applied to clean and dry surface by automatic mechanical means.
- In order to avoid entrapped air-bubbles, excessive tension and shear, the customer should determine appropriate lamination conditions.
- The best lamination conditions are obtained at a temperature between 15 °C and 40 °C.

Application guidelines

- In general, these tapes are immediately usable for further processing after lamination. It is not advisable to use these products on substrates containing copper.
- These tapes are not recommended to be use in heavy forming processes.
- SPV 3088A5 cannot be used for outside exposure.
- Surface protection tapes are not meant for permanent protection, they should be removed at the end of the supply chain.

If you require additional information on technical properties and application as well as product sampling or testing, please contact your local Nitto Europe sales office.

General conditions of use and precautions:

The properties of the product might be adversely affected by various elements such as composition, condition and surface of and impurities in or on the substrate, temperature and humidity during storage and the surrounding environment at and after application and time of exterior use. When the product is used in combination with another material or process, the user shall assure the compatibility of the product in such combination and whether this combination results in the expected performance. The same principle applies in the event of product use in extreme conditions or circumstances, whether at or after the moment of application, including extended exposure to sunlight or extreme temperatures and pressure.

Packaging, transport and storage:

During transport and storage the product should always be protected against direct sunlight and extremes in temperature and humidity and contained in its original packaging. Once removed from its packaging, it should be promptly applied and remain shielded from direct sunlight and extreme temperature as well as protected against dust and other impurities.

Liability:

Except for its wilful misconduct, Nitto Europe's liability shall be limited to a replacement, a reimbursement or an additional delivery of the product, and shall not exceed the purchase price of the products. In no event shall Nitto be liable in respect of any indirect or consequential damages, including loss of profits. The above limitations of liability shall equally apply if Nitto Europe has assisted in any manner with the selection, treatment or application of the product.

Product information:

This datasheet provides a general description of the product properties and application scope. Full technical details in connection with this product are presented in the customer product specification, which is available upon request.

Edition: December 2007

Code: DS/12.07/A3 SPV 30800 series ENG

This datasheet replaces all previous versions

Nitto Europe NV has obtained following certificates:

- ISO 9001
 - ISO 14001
 - ISO/TS 16949
- Please check our website for applicable scope



For your local Nitto Europe sales office, please visit our web site:

www.nittoeurope.com

Please be advised that the information reflected in this datasheet is subject to change and the product described herein may be modified or discontinued without notice. Copyright © 2007 NITTO EUROPE NV. All rights reserved.