

Product Data Sheet

Edition 8.1.2008
 Identification no. 440
 Sikaflex-15 LM

Sikaflex®-15 LM

High-performance, low-modulus elastomeric sealant



Description Sikaflex-15 LM is a low-modulus, high-performance, 1-component, polyurethane-based, non-sag elastomeric sealant. Meets Federal Specification TT-S-00230C, Type II, Class A; ASTM C-920, Type S, Grade NS, Class 100/50, use T, NT, G, M; Federal Specification for silicones - TT-S-001543 A, Type non-sag. Tested in accordance with ASTM C-1382 for use in EIFS systems.

- Where to use**
- Excellent for moving joints in vertical applications.
 - Suitable for use between similar as well as dissimilar materials.
 - Typical applications include joints in concrete panel and wall systems, around window and door frames, reglets, flashing, common roofing detail applications, etc.
 - Exceptional sealant choice for high-rise and facade applications where high movement capability is required.
 - An effective sealant for use in Exterior Insulation Finish Systems (EIFS).

- Advantages**
- Low modulus of elasticity.
 - Easy and ready to use.
 - Eliminates time, effort, waste, and equipment clean-up.
 - Cures to a durable, flexible consistency.
 - Exceptional cut and tear resistance.
 - Stress relaxation properties.
 - Excellent adhesion.
 - Bonds to most construction materials without a primer.
 - Paintable with water-, oil- and rubber based paints.
 - Excellent resistance to aging, weathering.
 - Jet fuel resistant.
 - Proven in tough climates around the world.
 - Non-leaching.
 - Capable of +100% / -50% joint movement.
 - Two-hour UL fire rating when used with Ultra Block®.

Coverage 10.1 fl. oz. cartridge seals 12.4 lineal ft. of 1/2 in. x 1/4 in. joint. 20 fl. oz. uni-pac sausage seals 24 lineal ft. of 1/2 in. x 1/4 in. joint.

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

Shelf Life	10.1 fl. oz. cartridges	12 months
	20 fl. oz. uni-pac sausages	12 months
	5 gal. pails	6 months
	55 gal. drums	6 months
Storage Conditions	Store at 40°-75°F. Condition material to 65°-75°F before using.	
Colors	White, Colonial White, Aluminum Gray, Limestone, Black, Dark Bronze, Capitol Tan, Off-White, Beige, Almond, Coping Stone, Aluminum Stone, Medium Bronze, Redwood Tan, Hartford Green, Cedar, and Stone. Special colors on request (min. volume).	
Application Temperature	40° to 100°F. Sealant should be installed when joint is at mid-range of its anticipated movement.	
Service Range	-40° to 170°F (-40° to 75°C)	
Curing Rate	Tack-free time	3 to 6 hours (TT-S-00230C)
	Tack-free to touch	3 hours
	Final cure	7 to 10 days
Recovery	>80%	
Shore A Hardness (ASTM D-2240)	21 day	25 ± 5
Tensile Properties (ASTM D-412)		
	21 day	
	Tensile Stress	125 psi (.86 MPa)
	Elongation at Break	700%
	Modulus of Elasticity	25% 20 psi (.13 MPa)
		50% 35 psi (.24 MPa)
		100% 50 psi (.34 MPa)
Adhesion in Peel (TT-S-00230C)		
	Substrate	Peel Strength
	Aluminum	25 lb.
	Glass	25 lb.
	Concrete	30 lb.
		Adhesion Loss
		0%
		0%
		0%
Weathering Resistance	Excellent	
Chemical Resistance	Good resistance to water, diluted acids, and diluted alkalines. Not normally for fully immersed conditions. Consult Technical Service for specific data.	



Packaging Disposable 10.1 fl. oz., moisture-proof composite cartridges, 24/case; and uni-pac sausages 20 fl. oz., 20/case. Available on special order: 5 gal. pails, 55 gal. drums.

How to Use

Surface Preparation Clean all surfaces. Joint walls must be sound, clean, dry, frost-free, and free of oil and grease. Curing compound residues and any other foreign matters must be thoroughly removed. Install bond breaker tape or backer rod to prevent bond at base of joint.

Linear Feet of Sealant per Gallon

Inches	Depth					
	1/4	1/2	3/4	1	1 1/4	1 1/2
1/4	308.0					
1/2	154.0	77.0				
3/4	102.7	51.3	34.2			
1	77.0	38.5	25.7	19.3		
1 1/4	61.6	30.8	20.5	15.4	12.3	
1 1/2	51.3	25.7	17.1	12.8	10.3	8.6

Width

Priming Priming is typically not necessary. Most substrates only require priming if testing indicates a need, i.e. due to excessively porous substrate. Consult Sikaflex Primer Technical Data Sheet or Technical Service for complete information as to primer requirements.

Note: Most Exterior Insulation Finish Systems (EIFS) manufacturers recommend the use of a primer. When EIFS manufacturer specifies a primer or if on-site bond testing indicates a primer is necessary, Sikaflex 429 primer is recommended. On-site adhesion testing is recommended with final system prior to the start of a job.

Application Recommended application temperatures, 40°-100°F. For cold-weather applications, pre-conditioning units to approximately 70°F is recommended. Only apply sealant to clean, sound, dry, and frost-free substrates. Sikaflex-15 LM should be applied into joints when joint slot is at mid-point of its designed expansion and contraction.

Place nozzle of gun into bottom of the joint filling entire joint. Keep nozzle in the sealant, and continue on with a steady flow of sealant preceding the nozzle to avoid air entrapment.

Avoid overlapping of sealant to eliminate entrapment of air.

Tool sealant to ensure full contact with joint walls and remove air entrapment. Joint dimension should allow for 1/4 inch minimum and 1/2 inch maximum thickness for sealant. Proper design is 2:1 width to depth ratio.

- Limitations**
- Allow 1 week cure at standard conditions when using Sikaflex-15LM in total water immersion situations and prior to painting.
 - Maximum depth of sealant must not exceed 1/2 in.; minimum depth is 1/4 in.
 - Do not cure in the presence of curing silicone sealants.
 - Avoid contact with alcohol, and other solvent cleaners, during cure.
 - When overcoating, an on site test is recommended to determine compatibility.
 - Do not apply when moisture-vapor-transmission condition exists from the substrate, as this can cause bubbling within the sealant.
 - Use opened cartridges and uni-pac sausages the same day.
 - When applying sealant, avoid air-entrapment.
 - Since system is moisture-cured, permit sufficient exposure to air.
 - White color tends to yellow slightly when exposed to ultraviolet rays.
 - Light colors can yellow if exposed to direct gas fired heating elements.
 - The ultimate performance of Sikaflex-15 LM depends on good joint design and proper application. With joint surfaces properly prepared and sealed, movement of +100% -50% can be tolerated.
 - Do not use in contact with bituminous/asphaltic materials.

Caution

Combustible Keep away from open flames and high heat. Contains xylene; avoid breathing vapors. Use with adequate ventilation.

Irritant Avoid skin and eye contact. Use of NIOSH approved organic vapor respirator, safety goggles, and chemical-resistant gloves recommended. Remove contaminated clothing and shoes.

First Aid In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes; contact physician. Wash clothing before re-use. Discard contaminated shoes.

Clean Up Uncured material can be removed with approved solvent. Cured material can only be removed mechanically. For spillage, collect, absorb, and dispose of in accordance with current, applicable local, state, and federal regulations.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY
 All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikacorp.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikaconstruction.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEVABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikaconstruction.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
 201 Polito Avenue
 Lyndhurst, NJ 07071
 Phone: 800-933-7452
 Fax: 201-933-6225

Sika Canada Inc.
 601 Delmar Avenue
 Pointe Claire
 Quebec H9R 4A9
 Phone: 514-697-2610
 Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
 Carretera Libre Celaya Km. 8.5
 Fracc. Industrial Balvanera
 Corregidora, Queretaro
 C.P. 76920
 Phone: 52 442 2385800
 Fax: 52 442 2250537



Sika and Sikaflex are registered trademarks. Made in USA. Printed in Canada.

